



Perrotts is a trading name of Textiles F.R. Ltd.

Textiles F.R. Limited incorporating Perrotts
Flame Retardancy Finishers & Consultants

Unit 4B, (30) Wharfedale Road
Euroway Trading Estate
Bradford
West Yorkshire
BD4 6SG

Tel: 01274 651230
Fax: 01274 651305

E-mail: sales@textilesfr.co.uk
Web site: www.textilesfr.co.uk



Test Report & Certificate

UKAS TESTING LABORATORY No.1413

British Standard Flammability Test Document: 16804

Page 1 of 1

Test Method : BS EN ISO 15025:2002

Specification: BS5867-2:2008:Type B

Contract Curtain Test

Customer Account: ELI012
ELITIS
2 BIS RUE
JEAN RODIER
31 400 TOULOUSE
FRANCE

Order Details
TFR Order No : 195133
Customer Order : LM
Order Date : 04/08/2011
Fabric Description : TV545
Fabric Composition : 100% TREVIRA CS
Quantity (metres) : 1.0

Sample Conditioning : Test specimens were conditioned in an atmosphere having a temperature of 20°C +/- 2°C and Relative Humidity 65% +/- 5% for a minimum of 24 hours prior to testing.
Test Enclosure Conditions : Temperature 19 °C Relative Humidity 69 %
Cleansing Procedure : Flammability testing was performed without the durability requirements stated in Section 5 of BS5867-2:2008 being completed.
Other Details :
Sample Treatment : Sample tested in an as received state

Test Procedure: Six specimens were prepared each measuring 200mm +/- 2mm x 160mm +/- 2mm, three with the longer dimension in the length and three with the longer dimension in the width. A butane flame was applied to the sample face for 15 seconds.

Report Notes: This test was carried out in accordance with BSEN ISO 15025 Procedure A. The results may not apply to situations where there is a restricted air supply or prolonged exposure to large sources of heat such as in a conflagration.

Table with 7 columns: OBSERVATIONS, Warp Direction (Rep1, Rep2, Rep3), Weft Direction (Rep1, Rep2, Rep3). Rows include Flame reached an edge, Hole reached an edge, and Flaming debris, all with 'No' results.

Comments:

COMPLIANCE REQUIREMENTS: No part of any hole nor any part of the lowest boundary of any flame shall reach the upper edge or either vertical edge of any specimen and there shall be no separation of flaming debris from any specimen.

The sample complied with the requirements for BS5867-2:2008:Type B Flammability testing was performed without the durability requirements stated in Section 5 of BS5867-2:2008 being completed.

Conducted by : Mr.P. TAYLOR Laboratory Technician Date 08/08/2011
Authorised by: Miss K. BUTTON Office Manager Date 08/08/2011