



Perrotts is a trading name of Textiles F.R. Ltd.

Unit 4B, (30) Wharfedale Road
Euroway Trading Estate
Bradford
West Yorkshire
BD4 6SG

Textiles F.R. Limited
Flame Retardancy Finishers & Consultants

Tel: 01274 651230
Fax: 01274 651305
E-mail: sales@textilesfr.co.uk
Web site: www.textilesfr.co.uk



Test Report & Certificate

UKAS TESTING LABORATORY No.1413

British Standard Flammability Test Document: 21084 Page 1 of 1
Test Method : BS EN ISO 15025:2002 Duplicate Document 2
Specification: BS5867-2:2008:Type B Contract Curtain Test

Customer Account: ELI012
ELITIS
2 BIS RUE
JEAN RODIER
31 400 TOULOUSE
FRANCE

Order Details
TFR Order No : 248711
Customer Order : EMAIL CM
Order Date : 09/11/2018
Fabric Description : TV563
Fabric Composition : 100% POLYESTER
Quantity (metres) : 1.0

Sample Conditioning : Test specimens were conditioned in an atmosphere having a temperature of 20°C +/- 2°C and Relative Humidity 65% +/- 5% for a minimum of 24 hours prior to testing.
Test Enclosure Conditions : Temperature 20 °C Relative Humidity 65 %
Cleansing Procedure : Flammability testing was performed without the durability requirements stated in Section 5 of BS5867-2:2008 being completed.
Other Details :
Sample Treatment : Sample tested in an as received state

Test Procedure:
Six specimens were prepared each measuring 200mm +/- 2mm x 160mm +/- 2mm, three with the longer dimension in the length and three with the longer dimension in the width. A butane flame was applied to the sample face for 15 seconds.

Report Notes:
This test was carried out in accordance with BSEN ISO 15025 Procedure A. The results may not apply to situations where there is a restricted air supply or prolonged exposure to large sources of heat such as in a conflagration.

Table with columns: OBSERVATIONS, Warp Direction (Rep1, Rep2, Rep3), Weft Direction (Rep1, Rep2, Rep3). Rows: Flame reached an edge, Hole reached an edge, Flaming debris.

Comments:

COMPLIANCE REQUIREMENTS: No part of any hole nor any part of the lowest boundary of any flame shall reach the upper edge or either vertical edge of any specimen and there shall be no separation of flaming debris from any specimen.

The sample complied with the requirements for BS5867-2:2008:Type B Flammability testing was performed without the durability requirements stated in Section 5 of BS5867-2:2008 being completed.

Conducted by : Mr.R. BERRY
Laboratory Technician
Authorised by: Miss K. BUTTON

Date 10/12/2018

Date 10/12/2018